

MVQ diet

Methyl-vinyl-silicone-rubber Standard colour: blue, similar RAL 5024

- Food-compliant MVQ; approval acc. FDA, recommended for approval acc. EU1935/2004
- Resistant to mineral oil, HFD-U and cold water
- · Applicable for Rod and Piston Seals, Wiper Seals and Static Seals

Properties	Value	Unit	DIN Standard
Hardness	84 ± 5	Shore A	DIN 53505
Density	1,503	g/cm ³	DIN EN ISO 1183-1
Compression set 22°C/72h		%	DIN ISO 815-1
Compression set 70°C/24h		%	DIN ISO 815-1
Compression set 175°C/24h	33,7	%	DIN ISO 815-1
Elongation at break	192	%	DIN 53504
Tensile strength	6,4	MPa	DIN 53504
100% modulus	5,3	MPa	DIN 53504
Rebound resilience	51	%	DIN 53512
Abrasion	108	mm ³	DIN 53516
Tear strength	10,2	N/mm	DIN 53515
min. service temperature	- 50	°C	
max. service temperature	+210	°C	

Confirmation according FDA

Hereby we, M. Wilhelmsen A/S, confirm, that all single components used for our compound named **«MVQ diet»** are listed on Code of Federal Regulation of U.S. Food and Drug Administration (FDA), Rockville MD.

They are mentioned under following subchapters: 21CFR 177.2600

Confirmation according EU1935/2004

The confirmation according FDA mentioned above provides an approval according EU1935/2004. Due to unavoidable

technical factors or due to the form of delivery of the elastomeric pre-materials traces of non-specified impurities could

be included. A compulsory test should be applied to the final product.

Allowed for contact with foods. Not permitted for medical articles (implants).