

MVQ diet

Methyl-vinyl-silicone-rubber
Standard colour: transparent

- Food-compliant MVQ; approval acc. FDA, recommended for approval acc. EU1935/2004
- Resistant to mineral oil, HFD-U and cold water
- Applicable for Static Seals

Properties	Value	Unit	DIN Standard
Hardness	79 ± 5	Shore A	DIN 53505
Density	1,18	g/cm ³	DIN EN ISO 1183-1
Compression set 22°C/72h		%	DIN ISO 815-1
Compression set 70°C/24h		%	DIN ISO 815-1
Compression set 175°C/24h	20	%	DIN ISO 815-1
Elongation at break	320	%	DIN 53504
Tensile strength	8,9	MPa	DIN 53504
100% modulus		MPa	DIN 53504
Rebound resilience	38	%	DIN 53512
Abrasion		mm ³	DIN 53516
Tear strength	18	N/mm	DIN 53515
min. service temperature	- 50	°C	
max. service temperature	+210	°C	

Confirmation according FDA

Hereby we, M. Wilhelmsen A/S, confirm, that all single components used for our compound named «MVQ diet» are listed on Code of Federal Regulation of U.S. Food and Drug Administration (FDA), Rockville MD.

They are mentioned under following subchapters: **21CFR 177.2600**

Confirmation according EU1935/2004

The confirmation according FDA mentioned above provides an approval according EU1935/2004. Due to unavoidable technical factors or due to the form of delivery of the elastomeric pre-materials traces of non-specified impurities could be included. A compulsory test should be applied to the final product.

Allowed for contact with foods. Not permitted for medical articles (implants).

All above stated data results from random tests which were taken from the ongoing production. All data was established based on standard test-products according to ISO, DIN and ASTM standards and can basically not be carried over to the completed seal.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.